

Grade 94

Characteristics:

Ashless, Cotton

Physical Property	Standard Units		Metric Units	
Basis Weight	lbs/1389ft ²	27.0	gsm	94.8
Basis Weight	oz/yd ²	2.80		
Thickness	mils	7.5	mm	0.1905
Rapidity			mls/min	4.0
Frazier Permeability	cfm/ft ²		L/m ² /sec	
Tensile Strength MDT Dry	lb/in	21.5	N/m	3765
Tensile Strength CDT	lb/in		N/m	
Retention	micron	1.5		
Wet Burst	in	25.0	cm	63.5

Micron ratings are based on an Ahlstrom test method where 98% of a particulate size is removed during gravitational filtration. Micron rating values vary between industries and manufacturers depending on the test procedure.

Contact office:

Ahlstrom Filtration LLC
Mount Holly Springs
122 West Butler Street
Mt Holly Springs, PA 17065
USA
T: +1 717 486 3438
F: +1 717 486 6413

www.ahlstrom.com

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as Ahlstrom deems appropriate. Refer to www.ahlstrom.com for contact information.