

Grade 609

Characteristics:

White, smooth surface, cellulose

Physical Property	Standard Units		Metric Units	
Basis Weight	lbs/1389ft ²	28.0	gsm	98.3
Basis Weight	oz/yd ²	2.90		
Thickness	mils	9.0	mm	0.2286
Rapidity			mls/min	70.0
Frazier Permeability	cfm/ft ²		L/m ² /sec	
Tensile Strength MDT Dry	lb/in	19.6	N/m	3433
Tensile Strength CDT	lb/in		N/m	
Retention	micron	4.0		
Wet Burst	in	16.0	cm	40.6

Micron ratings are based on an Ahlstrom test method where 98% of a particulate size is removed during gravitational filtration. Micron rating values vary between industries and manufacturers depending on the test procedure.

Contact office:

Ahlstrom Filtration LLC
 Mount Holly Springs
 122 West Butler Street
 Mt Holly Springs, PA 17065
 USA
 T: +1 717 486 3438
 F: +1 717 486 6413

www.ahlstrom.com

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as Ahlstrom deems appropriate. Refer to www.ahlstrom.com for contact information.