

DATA SHEET

Description

The CE-Force Basic Shoe Covers are a disposable foot barrier for typical daily use. They are fluid resistant and easy to put on or take off. These shoe covers are constructed with triple-elastic runs for perfect fit and to prevent tripping. They are available with or without the anti-skid tread.

Composition

The CE-Force Basic Shoe Covers are made with lightweight and breathable spunbond polypropylene nonwoven fabric. The fabric provides liquid resistance and breathability.

These shoe covers have two elastomer elastic runs on the sides as well as a third one on the sole completely covered by fabric. They have no stitches neither on the sides nor on the sole, all seams are ultrasonically welded to reduce particle shedding. They are latex and silicone free.



Made in Canada

Physical Properties

- Breathable fabric
- Fabric weight: 35gsm
- Color: Medical Blue
- Fluid resistant
- Elastomer elastics
- Low linting
- Anti-skid
- Ultrasonically welded
- Latex and silicone free

Dimensions and Packaging

Thomas No.	Size	Dimensions (L x H)	Packaging
20A00G711	Universal	43 cm X 17 cm (16.93 in x 6.69 in)	150/Pk; 300/Cs
20A00G712	Ex-Large	47 cm x 17.75 cm (18.5 in x 6.99 in)	150/Pk; 300/Cs

Ideal Use

These CE-Force Shoe Covers are ideal for cleanrooms, pharmaceutical manufacturing, research facilities, GMP sites, labs or other clean environments requiring a foot barrier.

Notes

Storage Condition: Store in a cool and dry place
Country of origin: Canada

See reverse for more technical data and tests results

Material Physical Properties

Standard Applied	Test Method	Result
Coefficient of Friction <i>Machine Direction</i>	ASTM D1894-14 Static Kinetic	0.492 0.406
Coefficient of Friction <i>Cross Direction</i>	ASTM D1894-14 Static Kinetic	0.591 0.509
Breaking Strength and Elongation - Grab Test (lbf) <i>Machine Direction</i>	ASTM D5034-09(2017)	15.3
Breaking Strength and Elongation- Grab Test (lbf) <i>Cross Direction</i>	ASTM D5034-09(2017)	12.0
Trapezoid Tearing Strength (lbf) <i>Machine Direction</i>	ASTM D5587-15(2019)	8.9
Trapezoid Tearing Strength (lbf) <i>Cross Direction</i>	ASTM D5587-15(2019)	6.0
Ball Burst Strength (lbf)	ASTM D3787-16 MOD.	11.1
Helmke Drum Particle Count	IEST-RP-CC003.4	Category I

