

# TekniZorb Nonwoven Poly/Cel Cleanroom Wiper

# **Product Description**

Made with hydroentangled blend of 55% cellulose / 45% polyester; providing economical performance & purity. This creates a strong, clean, and very absorbant wipe for liquid removal or lint free wiping in controlled areas. This nonwoven wipe exhibits lower particle & fiber release than other comparable products via substrate & processing improvement & control. Class 100 packaged

# **Composition & Attributes**

- \* Light weight Hydroentangled 55% Cellulose / 45% Polyester Nonwoven wipe
- \* Low particle and fiber generation
- \* Extremely high absorbancy per basis weight
- \* Maintains hi strength in wet applications
- \* Works well with IPA and other cleaning solvents

#### **Applications**

- \* Ideal for spill pick up in controlled environments or gown room wipe
- \* Excellent choice for general purpose wiping; clean & economical
- \* Soft texture for scratch sensitive surfaces & very durable
- \* Autoclavable for Aseptic environments
- \* Compatible with ISO Class 6+ (Class 1000) cleanroom environments

Purity Specifications			<u>Maximum</u>	<b>Typical</b>	
* Particles & Fibers					
particles/m <sup>2</sup> fibers/m <sup>2</sup>			80 x 10 <sup>(6)</sup> 0.26 x 10 <sup>(6)</sup>	47 x 10 <sup>(6)</sup> 0.18 x 10 <sup>(6)</sup>	
* Nonvolatile Residue					
g/m <sup>2</sup> /ug/cm <sup>2</sup>	IPA Extractant		0.006 / 0.6	0.0038 / 0.38	
g/m <sup>2</sup> /ug/cm <sup>2</sup>	DIW Extractant		0.07 / 7.0	0.043 / 4.3	
* Extractable lons					
ppm / ug/g	Calcium (Ca+)		<30	18.5	
ppm / ug/g	Chloride (CI-)		<30	9.7	
ppm / ug/g	Potassium (K+)		<30	10.2	
ppm / ug/g	Magnesium (Mg <sup>2</sup> +)		<50	33.2	
ppm / ug/g	Sodium (I	Na+)	<50	25.6	

#### **Ordering Information**

Product
TZ1PCS2-9

TZ1PCS2-99 TZ1PCS2-1212 Size 9" x 9" (22.9cm x 22.9cm) 12" X 12" (30cm x 30cm)

# **Physical Properties**

\* Basis Weight 56g/m<sup>2</sup> (+/-4g/m<sup>2</sup>)

\* Material 55% Cellulose/45% Polyester

\* Absorbency Extrinsic Capacity: >280ml/m<sup>2</sup>

Intrinsic Capacity: >4.0ml/g Sorptive Rate: < 1 second

### **Test Method**

Orbital Shake Test	IEST-4.3-6.1.4	
	IEST-4.3-6.2.2	
Short Term Extraction	IEST-4.3-7.1.2	

Standard Extractable IEST-4.3-7.2.2.1B



#### **Packaging**

300 Ea/Bag 10 Bag/Case 150 Ea/Bag 10 Bags/Case



Connect With Us:





