

WA209 & WA212

SATURIX WA209 and WA212 consists of spunlace microfibre wipers saturated with a blend of 70% isopropanol alcohol and 30% deionized water in a resealable polyethylene pouch.

Wiper Material:	100% Microfibre
Wiper Construction:	Spunlace
Saturation Solution:	70% Isopropanol / 30% Deionized Water

Wiper Properties	Typical Value	Test Method
Basis Weight		
(oz/yd ²)	1.3	
(g/m ²)	44	
Nonvolatile Residue (NVR) (g/m²)		
Deionized Water	0.0182	IEST-RP-CC004.3
Isopropyl Alcohol	0.0343	IEST-RP-CC004.3
(ppm)		
Sodium	102	IEST-RP-CC004.3
Chloride	78	IEST-RP-CC004.3
Particles (million/m²)		
>0.5 µm	94	IEST-RP-CC004.3
Fibers (fibers/m²)		
>100 µm	17500	IEST-RP-CC004.3

Notes:

Data shown are typical data values for the wiper material in an unsaturated state. These values should not be used as product specifications.